

## Q8 Ravel D

### Application

- A solvent deposited soft film protective
- After evaporation of the solvent a soft thin protective layer is obtained which is suitable for long term protection

### Benefits

- Soft and thin protective layer
- Easy to apply by brushing or spraying
- Suitable for protection of ferrous and non-ferrous components
- Easy removal of the protective layer
- Protection time, minimum 12 months

| Properties                 | Method | Unit               | Typical |
|----------------------------|--------|--------------------|---------|
| Absolute Density, 15 °C    | D 4052 | g/ml               | 0.830   |
| Kinematic Viscosity, 40 °C | D 445  | mm <sup>2</sup> /s | 3.5     |
| Flash Point, P-M           | D 93   | °C                 | 48      |
| Type Protective Layer      |        |                    | oily    |

*The figures above are not a specification. They are typical figures obtained within production tolerances.*