

Q8 Ruysdael WR 2

Application

- Universal grease for lubrication of heavily loaded plain- and roller
- bearings at normal temperatures and limited speeds as well as for
- the lubrication of water pumps, chassis etc.

Specifications

 Q8 Ruysdael WR 2 classifications: DIN 51502 KP2K-20 ISO 6743 ISO-L-XBCIB2

Benefits

- Excellent adhesion properties
- Extremely good water resistance
- Long service life
- Rust protection under dynamic and static conditions
- Suitable for heavily loaded plain- and roller bearings at normal temperatures
- (to +90 °C for WR 0, to +100 °C for WR 1, and to +120 °C for WR 2) and limited speeds

| Properties | Method | Unit | Typical |
|--|-----------|--------|---------|
| Soap type | - | - | |
| Consistency, NLGI No. | | | NLGI 2 |
| Penetration, Worked, 25 °C, | | | |
| 150 g, 5 s | D 217 | | |
| 60 strokes | - | 0.1 mm | 286 |
| 10000 strokes | - | 0.1 mm | 281 |
| Copper Corrosion, 100 °C, 24 h | D 4048 | - | pass |
| Dropping Point | D 566 | °C | 150 |
| SKF Emcor Test, Distilled Water | ISO 11007 | - | pass |
| SKF Emcor Test, WWO, dist. water | - | - | pass |
| SKF Emcor Test, WWO, synth. salt water | - | - | - |
| SKF R2F Conditions A | - | - | pass |
| SKF R2F Test, conditions B, 120 °C | - | - | pass |
| SKF WBG test, vibrated | - | - | pass |
| Water Washout Resistance, | D 1264 | % | < 5 |
| Kin. Viscosity Base Oil at 40 °C | D 445 | mm²/s | 790 |

The figures above are not a specification. They are typical figures obtained within production tolerances.



